

Target Values

Ancora® C2S

English (mils, lbs/3msf)	nominal	8-120	*9-138	10-144	12-167	14-188	16-203	18-220	20-240	22-265	24-286
Basis Weight	lbs/3msf	120	138	144	167	188	203	220	240	265	286
Brightness (Both Sides)	GE	90	90	90	90	90	90	90	90	90	90
Caliper	mils	8.0	9.4	10.0	12.0	14.0	16.0	18.0	20.0	22.0	24.0
b* Color (Both Sides)	Spectro	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Smoothness (Both Sides)	Sheffield	6	6	6	8	10	12	12	13	14	15
Plybond	lbs/in ²	56	56	56	52	48	48	48	48	48	48
Stiffness - CD	Taber g-cm	20	25	35	50	70	105	130	175	230	255
Stiffness - MD	Taber g-cm	35	50	60	90	130	185	250	325	410	510

Metric (µm, g/sq m)	nominal	203-195	239-225	254-234	305-272	356-306	406-330	457-358	508-391	559-431	610-465
Basis Weight	gsm	195	225	234	272	306	330	358	391	431	465
Caliper	microns	203	229	254	305	356	406	457	508	559	610
Plybond	kPa	386	386	386	359	331	331	331	331	331	331
Stiffness - CD	L&W mN	41	51	71	102	142	213	264	355	467	518
Stiffness - MD	L&W mN	71	102	122	183	264	376	508	660	832	1035

* Conforms to USPS specifications