
Target Values: Candesce® C1S Paperboard (Arkansas)

English (mils, lbs/3msf)	nominal	10-129	12-143	14-163	16-182	18-199	20-217	22-233	24-250	26-273
Metric (µm, g/sq m)	nominal	254-210	305-233	356-266	406-297	457-324	508-354	559-380	610-408	660-444
Caliper	mils	10	12	14	16	18	20	22	24	26
Basis Weight	lbs/3msf	129	143	163	182	199	217	233	250	273
Brightness	GE	88	88	88	88	88	88	88	88	88
Coated 'b' Color	Spectro	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Coated Smoothness	Sheffield	10	12	15	18	19	21	23	25	27
Parker Print	microns	1.10	1.10	1.10	1.10	1.10	1.07	1.07	1.05	1.05
Plybond	lbs/in ²	70	55	45	40	39	39	39	39	38
Stiffness - MD	Taber g-cm	48	78	115	165	225	290	380	480	550
Stiffness - CD	Taber g-cm	24	36	56	82	115	145	190	225	250

Stiffness values represent end-of-machine testing.
These values may change.

Document Revision Date: July 2011

TECH DIRECT
1-877-805-8120