

Target Values

Candesce® Blister

English (mils, lbs/3msf)	nominal	.012-143	.014-163	.016-182	.018-199	.020-217	.021-225	.024-250	.026-273
Metric (µm, g/sq m)	nominal	305-233	356-266	406-297	457-324	508-354	559-380	610-408	660-444
Basis Weight	lbs/3msf	143	163	182	199	217	225	250	273
Brightness	GE	88	88	88	88	88	88	88	88
Caliper	mils	12	14	16	18	20	21	24	26
Coated 'b' Color	Spectro	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Coated Smoothness	Sheffield	15	19	20	25	25	25	30	32
Plybond	lbs/in ²	42	38	34	34	32	33	34	34
Stiffness - CD	Taber g-cm	45	55	90	110	140	160	220	250
Stiffness - MD	Taber g-cm	90	125	165	210	265	295	420	490

Candesce® Skin

English (mils, lbs/3msf)	nominal	.020-205	.024-242
Metric (µm, g/sq m)	nominal	508-334	610-394
Basis Weight	lbs/3msf	205	242
Brightness	GE	86	86
Caliper	mils	20.0	24.0
Coated 'b' Color	Spectro	1.5	1.5
Uncoated Smoothness	Sheffield	203	213
Plybond	lbs/in ²	36	36
Stiffness - CD	Taber g-cm	130	195
Stiffness - MD	Taber g-cm	260	400



Target Values

Candesce® Foldover C2S Blister

English (mils, lbs/3msf)	nominal	.014-169	.016-187	.018-206	.020-224	.021-231	.024-256	.026-279
Metric (µm, g/sq m)	nominal	356-275	406-304	457-335	508-365	533-376	610-417	660-454
Basis Weight	lbs/3msf	169	187	206	224	231	256	279
Brightness	GE	88	88	88	88	88	88	88
Caliper	mils	14	16	18	20	21	24	26
Coated 'b' Color	Spectro	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Coated Smoothness	Sheffield	19	20	25	25	25	30	32
Plybond	lbs/in ²	40	36	36	34	35	36	36
Stiffness - CD	Taber g-cm	55	90	110	140	160	220	250
Stiffness - MD	Taber g-cm	125	165	210	265	295	420	490